


## Connor

Item number 41154, KMAT 61000383




### Product description

Connor is an all-rounder that is very versatile. It combines a natural wool look with the durability and price advantage of polyester. Connor can be used as upholstery and decorative fabric and has good sound absorption (class B). The light fastness is above average with a grade of 5-6. The polyester fabric gets its natural wool look from a melange yarn, which produces both calm and contrasting tones thanks to the twill weave. There are no limits to the use of Connor. At the window, as a cushion or upholstery cover, in the hotel, in the office, in the restaurant or on a cruise ship, Connor is the right choice everywhere with its functionality and look.

### Technical Details

<b>Fabric width</b>	approx. 140 cm
<b>Weight je m<sup>2</sup></b>	approx. 350 g/m <sup>2</sup>
<b>Composition</b>	100% Polyester FR
<b>Flame retardancy</b>	IMO 2010 FTP Code Part 8, M 1, 1 / M, C 1, BS 5852 CRIB 5, BS 5867 Typ B, EN 13773, DIN EN 1021-2, DIN EN 1021-1, DIN 4102 / B1, CAL TB 117, NFPA 260 Flammability performance is dependant on the foam used.
<b>Light fastness</b>	note 5-6
<b>Wash fastness 40°C DIN EN ISO 105-C06</b>	note 5
<b>Wash fastness 60°C DIN EN ISO 6330 DIN EN ISO 5077</b>	note 5

<b>Wash fastness 72°C</b> DIN EN ISO 6330 DIN EN ISO 5077	note 4-5
<b>Dimensional change Washing 40°C</b> DIN EN ISO 6330 DIN EN ISO 5077	warp approx. +/-1%, weft approx. +/-1%
<b>Dimensional change Washing 60°C</b> DIN EN ISO 6330 DIN EN ISO 5077	warp approx. +/-2%, weft approx. +/-1%
<b>Dimensional change Washing 72°C</b> DIN EN ISO 6330 DIN EN ISO 5077	
<b>Rubbing fastness</b> DIN EN ISO 105-X12	dry: note 5, wet: note 4-5
<b>Abrasion to Martindale</b> DIN EN ISO 12947-2 DIN EN 14465-2006	approx. 70000 rubs
<b>Pilling</b> DIN EN ISO 12945-2	Note 4-5 at 2000 rpm
<b>Measured sound absorption coefficient</b> DIN EN ISO 354/DIN EN ISO 11654	0.8
<b>Sound absorption</b>	Class B
<b>Care labelling</b>	
<b>State</b>	2024-04-19