

## Mila

Item number 28699, KMAT 61000251




### Product description

Mila is a classic velour that is characterized by its matt shimmer and dense pile. The color palette consists of 28 typical velour colors. At 380 g/m<sup>2</sup>, it is a middleweight in the velour family. Mila is suitable for use both as an upholstery fabric and as a curtain. The velour Lea with 520 g/m<sup>2</sup> and Elba 250 g/m<sup>2</sup> are available in the same color palette.

### Technical Details

|   |  |
|---|--|
| <b>Fabric width</b>   | approx. 140 cm   |
| <b>Weight je m<sup>2</sup></b>                                | approx. 360 g/m <sup>2</sup>   |
| <b>Composition</b>  | 100% Polyester Trevira CS  |
| <b>Flame retardancy</b>                                       | IMO 2010 FTP Code Part 8, IMO 2010 FTP Code Part 7, M 1, C 1, BS 5852 CRIB 5, EN 13773, DIN EN 1021-2, DIN EN 1021-1, DIN 4102 / B1, DIN 4102 / B2, NFPA 701, CAL TB 117, NFPA 260, BS 5867 Typ C<br>Flammability performance is dependant on the foam used. |
| <b>Light fastness</b>   | note 5-6   |
| <b>Wash fastness 40°C<br/>DIN EN ISO 105-C06</b>              | note 4   |
| <b>Wash fastness 60°C<br/>DIN EN ISO 6330 DIN EN ISO 5077</b> | note 4-5   |
| <b>Wash fastness 72°C<br/>DIN EN ISO 6330 DIN EN ISO 5077</b> | note 2-3   |

|  |  |
|--|--|
| <b>Dimensional change Washing 30°C</b>   | warp approx. +/-1%, weft approx. +/-1%   |
| <b>Dimensional change Washing 60°C<br/>DIN EN ISO 6330 DIN EN ISO 5077</b>       | warp approx. +/-1%, weft approx. +/-1%   |
| <b>Rubbing fastness<br/>DIN EN ISO 105-X12</b>                                   | dry: note 4-5, wet: note 4   |
| <b>Abrasion to Martindale<br/>DIN EN ISO 12947-2<br/>DIN EN 14465-2006</b>       | approx. 100000 rubs  |
| <b>Pilling<br/>DIN EN ISO 12945-2</b>  | Note 4-5 at 2000 rpm   |
| <b>Measured sound absorption coefficient<br/>DIN EN ISO 354/DIN EN ISO 11654</b> | 0.75   |
| <b>Sound absorption</b>  | Class C  |
| <b>Care labelling</b>  |  |
| <b>State</b>   | 2024-04-24   |