



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Dalton, Georgia 30720
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Report Number 17-12079

DELIUS GmbH
Bielefeld, Germany

Test Number 4840-9161-1217R
July 20, 2016

Stain Resistance

Test Method: The material was tested in accordance with Federal Specification CCC-W-408D, *Wall Covering, Vinyl-Coated*, which covers the classification of wall covering according to its serviceability in use. A sample from an area with as many different printed colors as possible, as well as the ground, is exposed to the following reagents: (1) Distilled water, 75 ± 5°F; (2) Distilled water, 120 ± 5°F; (3) Ethyl alcohol; (4) Vinegar, 3 % acetic; (5) Alkali solution; (6) Hydrochloride, 5 %; (7) Soap solution; (8) Detergent solution; (9) Pure orange juice; (10) Butter; (11) Catsup; and (12) Tea. Immediately after application, the reagent is covered with a watch glass and allowed to stand for a period of 24 hours. After removal of the watch glass, the wall covering is cleaned using, as appropriate, hot or cold distilled water, 50 % ethyl alcohol, or with the specified detergent solution. The specimen shall show no evidence of appreciable change to the decorative surface.

Material Tested: The client submitted a sample of vinyl wall covering identified as **20 oz. Printed and Embossed Type II Osnaburg Backed Commercial Vinyl Wallcovering (YM)**.

Test Data:

Reagent	Rating	Reagent	Rating
(1) 75°F distilled water	5	(7) standard soap solution	5
(2) 120°F distilled water	5	(8) detergent solution	5
(3) 50% ethyl alcohol	5	(9) orange juice	5
(4) vinegar	5	(10) butter	5
(5) 1% NaOH solution	5	(11) catsup	5
(6) 5% HCl	5	(12) tea	4-5

Note: The rating system is based on the AATCC *Nomenclature for Subjective Rating Processes* in which a rating of 5 = negligible or no staining, 4 = slight staining, 3 = noticeable staining, 2 = considerable staining, and 1 = severe staining. A rating of less than 4 is considered "appreciable" in relation to severity of change.

Test Result: The material tested, **20 oz. Printed and Embossed Type II Osnaburg Backed Commercial Vinyl Wallcovering (YM)**, meets Type II requirements for stain resistance of Federal Specification CCC-W-408D. Overall classification can not be based on a single performance property.

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.