



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Dalton, Georgia 30720
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Report Number 17-12078.7

DELIUS GmbH
Bielefeld, Germany

Test Number 4782-7839-1217R
April 1, 2016

Tear Resistance

Test Method: The material was tested in accordance with Federal Specification CCC-W-408D, *Wall Covering, Vinyl-Coated*, which covers the classification of wall covering according to its serviceability in use. The test is conducted in accordance with ASTM Test Method D 751, Method A, using an Elmendorf tear tester. The result is reported as the scale reading.

Material Tested: The client submitted a sample of vinyl wall covering identified as **20 oz. Printed and Embossed Type II Osnaburg Backed Commercial Vinyl Wallcovering (YM)**.

Test Data:

Tear Resistance, Machine Direction — 54.0
Tear Resistance, Cross Machine — 29.6

Test Result: The material tested, **20 oz. Printed and Embossed Type II Osnaburg Backed Commercial Vinyl Wallcovering (YM)**, meets Type II requirements for tear resistance of Federal Specification CCC-W-408D. Overall classification can not be based on a single performance property.

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.