

DIVERSIFIED

TESTING LABORATORIES, INC.

WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET P.O. BOX 4004 BURLINGTON, NORTH CAROLINA 27215 PHONE (336) 227-7710 • FAX (336) 227-1175 www.diversifiedtestinglabs.com

February 25, 2021

Ms. Angelika Schmidt-Koch DELIUS GMBH & CO. KG Goldstraβe 16 – 18 33602 Bielefeld Germany

Reference:

Laboratory Test Report

Lab Identification No. 44628

Invoice No. 75879

Dear Ms. Schmidt-Koch:

One (1) sample, identified as **Article Fellini X Deligard**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

10mm

8mm

10mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

SEAL 1975 PARTIES OF CARGOTTO STATE OF THE PROPERTY OF THE PRO