



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 28, 2020

Ms. Angelika Schmidt-Koch
DELIUS GMBH & CO. KG
Goldstraße 16 – 18
33602 Bielefeld
Germany

Reference: Laboratory Test Report
Lab Identification No. 43174
Invoice No. 74400

Dear Ms. Schmidt-Koch:

One (1) sample, identified as **ARTICLE CONTRALUX 34057**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u> <u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	4.71
2	0.0	6.60
3	0.0	4.68
4	0.0	4.50
5	0.0	5.84
6	0.0	9.02
7	0.0	1.91
8	0.0	4.34
9	0.0	7.13
<u>10</u>	<u>0.0</u>	<u>9.44</u>
AVG	0.0	5.82

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

