

DIVERSIFIED

TESTING LABORATORIES, INC

WORLDWIDE SERVICE

-"We Test Per Your Request"-

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 18, 2019

Ms. Angelika Schmidt-Koch DELIUS GMBH & CO. KG Goldstraβe 16 – 18 33602 Bielefeld Germany

Reference: Laboratory

Laboratory Test Report

Lab Identification No. 38906

Invoice No. 70101

Dear Ms. Schmidt-Koch:

One (1) sample, identified as **ARTICLE BROOKS 41584**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

11_{mm}

14mm

10_{mm}

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr