

## DIVERSIFIED TESTING LABORATORIES, INC.

WORLDWIDE SERVICE

-"We Test Per Your Request"

336 WEST FRONT STREET P.O. BOX 4004 BURLINGTON, NORTH CAROLINA 27215 PHONE (336) 227-7710 • FAX (336) 227-1175 www.diversifiedtestinglabs.com

June 24, 2020

Ms. Petra Baumhoefner DELIUS GMBH & CO. KG Goldstraβe 16 – 18 33602 Bielefeld Germany

Reference:

Laboratory Test Report

Lab Identification No. 41718

Invoice No. 72942

Dear Ms. Baumhoefner:

One (1) sample, identified as **ARTICLE ARUBA DELIMAR**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

## **Test Results**

Vertical Char Lengths

22mm

20mm

18mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

SEAL 1975 SEAL 1975 STATE OF THE PROPERTY OF T